



Pond Pro 2000

Butyl Liquid Rubber Coating

Pondpro2000 is a specially formulated Butyl Liquid Rubber coating that provides excellent waterproofing and ultraviolet resistance, meeting the demands of submerged water, temperature fluctuations and seasonal thaws. With over 30 years of success, thousands of pond repair shops and DIY customers have trusted it as the one-stop solution to pond leaks and repairs. It adheres well to properly prepared surfaces. It is thermally stable and resists cracking and peeling under extreme weather. Its unique properties are in the manufacturing process. This product cures through a chemical cross-bond, meaning that as it dries, it chemically bonds to the surface it is applied to, allowing superior adhesion and longevity. There is no other pond sealant that has our unique solvent-curing process.

COVERAGE	DRYING TIME	ELONGATION	TENSILE STRENGTH
40 sq ft / gal	24 hours	400%	1200 PSI

IN THIS DOCUMENT

01	Type of applications	02	Technical data	03	Surface preparation
04	Application temperatures	05	Application methods	06	Handling & storage

01 Type of applications

Adheres to properly prepared:

◆ EPDM

◆ Concrete

◆ Metal

◆ Vinyl

◆ TPO

◆ Fiberglass

◆ Hypalon

◆ Foam

02 Technical data

PROPERTY	VALUE	UNIT
Coverage	40	sq ft per gallon
Flash point	101	°F
Weight	8.95	lb./gal.
Solids (% by weight)	56 ± 1	%
Viscosity @ 78 °F	4800	cps.
Drying time Temps 55 or above	24	hours
Fill pond after	72	hours
Elongation	400	%
Tensile strength	1200	PSI

03 Surface preparation

The surface must be free of oils, moisture, soil, and other contaminants that may interfere with proper adhesion. Remove loose material from seams and surface. Do not use any chemicals to clean the pond if you have fish in your pond. Water only to clean. If your pond is fish-free then you can use detergents.

04 Application temperatures

50° and Rising

For best results, keep ambient air and substrate temperatures between 50°F and 110°F

05 Application methods

- 1 Product must be mixed with electric drill for 3-4 minutes.
- 2 PondPro2000 can be applied with a 3/8-inch nap roller and paintbrush.
- 3 For seams that have separated, we suggest our butyl tape prior to the application of the PondPro2000.
- 4 For cracks and to fill into joints use our MS Butyl caulk prior to applying the PondPro2000.

06 Handling & storage

COMBUSTIBLE — HANDLE WITH CARE

Pond Pro 2000 contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information and precautions before using.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

PondPro2000

494 Bridgeport Ave, Suite 101-342, Shelton, CT 06484

END OF TECHNICAL DATA SHEET